

ONE-COMPONENT PAINT FOR PARQUETS (VERNICE PER PARQUET MONOCOMPONENTE)

**FV 2040 flat – FV 2099 gloss (FV 2040 opaco –
FV 2099 lucida)**

1) GENERAL INFORMATION AND INSTRUCTIONS FOR USE

1.1) General information:

Moisture-cure, polyurethane paint, glossy or flat, for wooden floors.

Product with very silky film and significant elasticity, excellent hardness and scratch-resistance.

Forms a film with excellent mechanical, chemical and aesthetic properties.

Can be used on any type of floor, even if previously painted. Note: In this case, however, we recommend doing a preliminary test on a small area.

1.2) Instructions for use:

Paint finish for interior walkable surfaces.

Product is ready for use.

2) IDENTIFICATION PROPERTIES

Type of resin: moisture-cure polyurethane
Specific weight: 980 g/litre \pm 10 g/litre
Yield: 5 – 6 m ² /l
Kinematic viscosity at 20°C: Ford viscosity cup/4 15" \pm 3"
Gloss meter: 90 \pm 5 gloss for FV 2099
Gloss meter: 40 \pm 5 gloss for FV 2040

3) APPLICATION INSTRUCTIONS

3.1) Ambient and substrate conditions

Ambient temperature:

minimum 5 °C maximum 40 °C

Ambient relative humidity:

maximum 80%

Rev.01

Updated on: MARCH 2015

Colorificio Feroni S.r.l.

PRODUCTION

Wood stains - Paints - Thinners

Substrate temperature: minimum 5 °C maximum 40 °C
Maximum humidity of substrate: for wood and wood derivative substrates: 15-20%

3.2) Application:

After properly preparing your parquet, filling any cracks with a suitable filler and sanding with a 120-150 grit sandpaper, thoroughly clean the surface you wish to paint and then, using a roller or a brush, apply two or three coats of ONE-COMPONENT PAINT FOR PARQUETS, depending on the type of wood treated.

3.3) Application with brush and roller

We recommend applying a MINIMUM of two coats, with a minimum 12 hour between coats, after sanding or scouring with steel wool.

Product is ready for use, if necessary thin 5 – 10% with POLYURETHANE THINNER 2009 (DILUENTE PER POLIURATANICI 2009) or THINNER 2008 FOR ACRYLICS (DILUENTE PER ACRILICI 2008).

Mix the product well before and during application.

Recommended yield, per layer: ≈ 5-6 m² litre

3.4) Drying or hardening at 23 °C and 65% relative humidity.

Surface dry or dry to touch time: 2 hours.

Dry to recoat time: minimum 2 hours.

Dry to sand: after 4 hours.

Dry to walk on: after 48 – 72 hours.

Drying times may vary according to temperature, ventilation and relative humidity.

The paint must be applied at a temperature of over 10°C (product, substrate, ambient).

3.5) Tool cleaning:

With POLYURETHANE THINNER 2009 (DILUENTE POLIURETANICO 2009)

4)

STORAGE INSTRUCTIONS

Maximum storage temperature: 40 °C

Minimum storage temperature: 5 °C

Package formats available: 1 l – 4 l

Rev.01

Updated on: MARCH 2015

5)

SAFETY INSTRUCTIONS

This product does not require EC labelling.
See updated safety data sheet.

This revision supersedes and replaces previous ones.

Although the above information is reliable, it must be considered as indicative. Its use does not imply any responsibility on our part. It is therefore the user's responsibility to assess in advance the suitability of the product for its intended use.

Rev.01 Updated on: MARCH 2015

Page 3 of 3

37050 Oppeano (VR) – Via Quaiotto, 18

Tel: 045 6970100 automatic line selection – Fax: 045 7135330 – info@feroni.it - www.feroni.it

Share Capital 100,000.00 Fully Paid-up - Register of Handicraft Enterprises 93780 – Register of Companies, Tax Code and VAT
No. 02997990235